

# TMR-3760

## Clear / White Translucent PVF Release Film

#### Features:

- TMR-3760 is a clear or white translucent PVF release film.
- Suitable for use with all commonly used resin systems up to 400°F (204°C).
- TMR-3760 is an excellent release film for mild contour and flat parts.
- Ideal for lying flat and smooth with little wrinkling as experienced with more pliable release films.
- Effective for use where inspection of the part before or after cure is desired.

#### Properties:

Technical Data:	Test Method:	Typical Value:
Maximum use temperature		400°F (204°C)
Color		Clear, White
Tensile Strength (at break)	ASTM D-882	> 10,000 PSI
Elongation (at break)	ASTM D-882	> 200%
Yield		1407ft <sup>2</sup> /lb/mil

The above values are "Typical Values" which have a nominal range about them and are not intended for specification purposes.

### Availability:

• Standard roll sizes: 54" x .001" x 3,000'

54" x .002" x 1,500'

• Alternative sizes available upon request (minimum order quantities may apply).

• Perforation: Please call for availability.

#### Storage:

• Store in original packaging and protect from the environment.

#### Health & Safety:

• Handling of these products must conform to individual company guidelines and health and safety regulations.

#### Technology Marketing, Inc.

P: 801.265.0111 • F: 801.265.0184 6122 Stratler Street • Salt Lake City, UT 84107 USA • customerservice@tmi-slc.com • <u>www.tmi-slc.com</u>

#### ISO 9001:2015 & AS9120B Certified

Note: Data provided is for information only and does not constitute any warranty for the product as the conditions and varying methods of use are beyond our control, Technology Marketing Inc. shall not be liable for any special indirect, incidental, or consequential damages, including without limitation, lost revenues or lost profits, which may result from the use or inability to use these materials. These materials are provided "as is" without warranty of any kind, either expressed or implied including, but not limited to the implied warranties of merchantability or fitness for a particular purpose