Product Data

Style TEF7 US System

Type of Yarns Warp Yarn: Thorstrand + ECG 150 1/0

Fill Yarn: Thorstrand + ECD 450 1/0

Fabric Weight, Dry 8.59 oz/yd² 291 g/m²

Weave Style 5 Harness Satin

Construction

 Nominal Construction
 Warp Count:
 32/in
 12.60/cm

 Fill Count:
 30/in
 11.81/cm

 Fabric Thickness
 11.6 mils
 0.29 mm

Important

All information is believed to be accurate but is given without acceptance of liability. All values have been generated from limited data. The values listed for weight, thickness and breaking strengths are typical greige values, unless otherwise noted. Users should make their own assessment of the suitability of any product for the purpose required. All sales are made subject to our standard terms of sales which include limitations on liability and other important terms. The fabric style listed may not be available from inventory and minimum order quantities may apply.

For More Information

Hexcel is a leading worldwide supplier of composite materials to aerospace and other demanding industries. Our comprehensive product range includes:

- Carbon Fiber
- Reinforced Fabrics
- Carbon, Glass, Aramid and Hybrid Prepregs
- RTM Materials

- HexTOOL[®] composite tooling material
- Structural Film Adhesives
- Honevcomb Cores
- Engineered Core

1913 North King Street Seguin, Texas 78155 Phone: 830-379-1580 Fax: 830-379-9544

Customer Service Toll Free: 1-866-601-5430

For European sales office numbers and a full address list, please go to:

http://www.hexcel.com/contact/salesoffices

Copyright © 2014 − ® Hexcel and Hexcel logo are registered trademarks of Hexcel Corporation, Stamford, Connecticut.

™ HexForce is a trademark of Hexcel Corporation, Stamford, Connecticut.



