

FLASH TAPE 2R

2 Mil High-Temp. Pressure Sensitive Rubber Adhesive Polyester Tape

Features:

- High temperature and pressure resistant rubber adhesive polyester tape.
- Recommended for long term temperature exposures over 350°F.
- Cleanly releases without leaving residue on metals and composite details.

Applications:

- All phases of masking operations where no residue can be tolerated.
- Ideal for holding release films, fabrics, bleeders/breather, metal, and composite details in place for pre-fit and pre-bond applications.

Properties:

| Technical Data: | Test Method: | Typical Value: |
|------------------------------|--------------|--------------------------------|
| Max. use temperature | - | 400°F (204°C) |
| Color | - | Green |
| Backing (Polyester) | - | .002 in. (.051 mm) |
| Adhesive (High-Temp. Rubber) | - | .002 in. (.051 mm) |
| Total Tape Thickness | - | .004 in (.0762 mm) |
| 180°F Peel Adhesion to Steel | - | 30 oz/in. width (.33 kg. /cm.) |
| Elongation (at Break) | - | 100% |

The above values are "Typical Values" which have a nominal range about them and are not intended for specification purposes.

Availability:

- Standard roll sizes: 1" x 72 yards and 2" x 72 yards
- Custom sizes available upon request (minimums may apply)

Storage:

- No special storage conditions

Health & Safety:

- Handling of these products must conform to individual company guidelines and health and safety regulations.

Technology Marketing, Inc.

P: 801.265.0111 • F: 801.265.0184

6122 Stratler Street • Salt Lake City, UT 84107 USA • customerservice@tmi-slc.com • www.tmi-slc.com

ISO 9001:2015 & AS9120B Certified

Note: Data provided is for information only and does not constitute any warranty for the product as the conditions and varying methods of use are beyond our control. Technology Marketing Inc. shall not be liable for any special indirect, incidental, or consequential damages, including without limitation, lost revenues or lost profits, which may result from the use or inability to use these materials. These materials are provided "as is" without warranty of any kind, either expressed or implied including, but not limited to the implied warranties of merchantability or fitness for a particular purpose